

FAQ

HOW TO DEAL WITH SELF-LEVELING SANDING

Cause the flooring hollowing and edge warping, because glue and self-leveling bond is not strong.

Reason analysis

- Construction in low temperature drying conditions
- Add too much water in self-leveling
- Primer is not incomplete sealed, self-leveling dehydrate too fast
- Wrong polish disc
- Self-leveling own problem, such as low-intensity self-leveling or failing self-leveling

Measures to avoid

Select appropriate self-leveling and standard construction

Solution

- Re-install another self-leveling layer
- Select a good permeability primer coat on self-leveling

